



4270119 ALIEN H. 1150 mm - LED 3000K Street optic

DISCONTINUED Item available until stocks are exhausted. Please check availability with our sales department.

## Lighting information

Source power type	LED
Colour temperature	3000K
CRI	>80
MCADAMS	3
LM 80/TM-21	L80B10@>60Kh
Source power	16,00 W
Nominal flux	2500 lm
Plug-in power	22,00 W
Real flux	1750 lm
Maximum intensity	470 cd/klm
Beam angle	Street optic
Power Supply Unit	220 ÷ 240V
Operating frequency	0/50/60 Hz
Power factor	0,95
Dimmable	Not dimmable
Safety class	II
Wiring	External
Cable section	2 x 1,00 mm <sup>2</sup>
Cable length	1.500 mm;
Cable type	H05RN-F
Protection Rating	IP66
Breaking Strength	IK 10
Energy efficiency class	A/A+/A++
Diffuser type	Transparent
<b></b>	extra-clear glass

Diffuser thickness 4 mm

## Colours

Standard colour

.08 Anthracite

### Colours available on request

.01	Black
.07	Corten

O.02 White .09 Bronze .06 Grey



## **Platek**<sup>®</sup>

PLATEK s.r.l. Via Paderno, 19 | 25050 Rodengo Saiano (BS) ITALY P.IVA 03320290178 | Codice fiscale 03007130176 Registro delle Imprese di Brescia n, 03007130176 REA 311057 Capitale sociale Euro 1.000.000,00 i.v. Società con unico socio






PLATEK s.r.l. Via Paderno, 19 | 25050 Rodengo Saiano (BS) ITALY P.IVA 03320290178 | Codice fiscale 03007130176 Registro delle Imprese di Brescia n. 03007130176 REA 311057 Capitale sociale Euro 1.000.000,00 i.v. Società con unico socio



# Product features

Extruded aluminium alloy body. Die-cast head made of aluminium alloy with very low copper content. A4 Stainless steel screws. Product supplied with inspection door. Gore valve to prevent condensing. The product is subjected to galvanic anodizing treatment divided into distinct phases: mechanical satin finishing, surface degreasing, anodic oxidation and finally fixing. Subsequently the product is painted by performing a double pass in-line process, which allows you to generate a single thick protective layer which then generates barrier against atmospheric agents and UV rays. This allows to achieve corrosion resistance performance in salt spray. Pre-treatment with atmospheric pressure plasma is carried out on the surface before gluing of the diffuser on Platek products.

## Technical dimensions



## Technical shipping information

Net weight	14,50 kg
Gross weight	17,00 kg
Packaging width	300,00 mm
Packaging height	300,00 mm
Packaging depth	1.350,00 mm

### 4270119 ALIEN H. 1150 mm - LED 3000K Street optic

# Lighting information



Plug-in power	22,00 W
Real flux	1750 lm
Maximum intensity	470 cd/klm
Beam angle	Street optic

### Lighting Simulation



### H. 1150 mm (12 m)

simulation made with ALIEN H. 1150 mm 22,0 W 3000K		
Optics:	Street optic	
Code:	4270119	
Distance between products:	12 m	



### H. 1150 mm (10 m)

simulation made with ALIEN H. 1150 mm 22,0 W 3000K		
Optics:	Street optic	
Code:	4270119	
Distance between products:	10 m	
Plug-in power	22,00 W	
Real flux	1750 lm	
Maximum intensity	470 cd/klm	
Beam angle	Street optic	

## **Platek**<sup>®</sup>

PLATEK s.r.l. Via Paderno, 19 | 25050 Rodengo Saiano (BS) ITALY P.IVA 03320290178 | Codice fiscale 03007130176 Registro delle Imprese di Brescia n. 03007130176 REA 311057 Capitale sociale Euro 1.000.000,0 i.v. Società con unico socio





PLATEK s.r.l. Via Paderno, 19 | 25050 Rodengo Saiano (BS) ITALY P.IVA 03320290178 | Codice fiscale 03007130176 Registro delle Imprese di Brescia n. 03007130176 REA 311057 Capitale sociale Euro 1.000.000,00 i.v. Società con unico socio



### The process of galvanisation and multi-coating protection

Platek goes well beyond the standards required for conventional protection processes, making use of its longstanding and in-depth expertise in aluminium alloys. All the aluminium components of the products - extruded, die-cast or turned - are subjected to a galvanic anodizing process in the phase following mechanical processing. The process increases their wear resistance and improves the adhesion of the paint. Galvanization involves three distinct phases: mechanical satin finishing and surface degreasing, anodic oxidation and fixing. After the first phase that eliminates any impurities, the aluminium body is immersed in special electrolytic tanks, in which the aluminium surface is transformed into aluminium oxide, which makes the metal more resistant. To respond optimally to the needs of the global market, all Platek products undergo a two-layer painting process. After preparation with washing and rinsing in accordance with the strictest environmental standards, the product is coated with an epoxy primer which guarantees, in addition to anodizing, an excellent degree of protection. The final step is the preparation of the polyester powder which gives the final velvety finish of the component. These last two phases, being done in a continuous cycle, form a single high-thickness layer that is resistant to the action of UV rays and atmospheric agents. This process allows corrosion resistance in salt fog that far exceeds the average standards of the market to be achieved.

#### The gluing process and plasma treatment

One of the most complex and delicate aspects in outdoor lighting products is the fitting of glass onto the lighting body. This must ensure over time an excellent degree of insulation from atmospheric agents, even in harsh environmental conditions, to maintain a stable performance with zero maintenance. The gluing process of the glass on Platek products is managed at an automated workstation, preceded by a pre-treatment of the surfaces with atmospheric pressure plasma. Pre-treatment modifies the characteristics and ionic properties of the treated surfaces, activates the polar materials at strategic points, removes any residue of detaching agents, such as silicones and oils with a precision microcleaning, favouring excellent wettability of the bonded surfaces and a stable seal in time. The gluing process of the glass with specific plasma treatment allows a bonding force four times greater than similar products to be obtained. The shaping of the surfaces is followed by the application of the silicone and the assembly of the glass onto the lighting body using an automated process that guarantees perfect sealing of the lamp.

#### Precise LED selection

All LEDS used by Platek, once assembled by trusted personnel are tested with suitable instruments to check the colour specification required by Platek standards. The choice of using only 3 McAdams colour steps and with a CRI value exceeding 90, provide a high level of light quality that is difficult to find in the world of outdoor lighting. As far as LED products are concerned, Platek has adopted a system of protection against electrostatic discharge along the entire production chain of electronic components to increase the resistance of circuits to power surges.



PLATEK s.r.l. Via Paderno, 19 | 25050 Rodengo Saiano (BS) ITALY P.IVA 03320290178 | Codice fiscale 03007130176 Registro delle Imprese di Brescia n. 03007130176 REA 311057 Capitale sociale Euro 1.000.000,00 i.v. Società con unico socio